



## RF Power Capacitors Class1 10kV Hi-Load Tag-Screw Mounting

<p><b>Morgan Advanced Materials</b> is a world leader in the design and manufacture of complex electronic ceramic components and assemblies used in a wide range of applications and cutting edge technologies. Morgan's Ruabon Division specialises in the development and production of dielectric and ferroelectric materials and components. This range of high voltage RF discs capacitors is fabricated from very low loss CLASS 1 ceramic dielectric materials which permit them to carry very high electrical loads over a wide frequency range.</p>	
<p><b>Applications include :</b></p> <ul style="list-style-type: none"> <li>• Radio Broadcast Transmitters</li> <li>• Induction and Dielectric Heating Equipment</li> <li>• HF Filter, By-Pass &amp; Coupling Circuits</li> <li>• High Power Matching Tuned Circuits</li> <li>• Antenna Circuits</li> <li>• Industrial Applications</li> <li>• High Power matching networks –Plasma Generators</li> <li>• High quality medical imaging systems (MRI)</li> </ul>	<p><b>Features :</b></p> <ul style="list-style-type: none"> <li>• Low loss Class 1 ceramic dielectric materials with noble metal electrodes resulting in low self heating.</li> <li>• High Voltage / High Reactive Power Ratings</li> <li>• Very low NPO capacitance-temperature characteristics available that result in correspondingly low tuned frequency drift.</li> <li>• Low Inductance construction permitting higher frequency use.</li> <li>• Low magnetic susceptibility</li> </ul>

Material Characteristics						
<b>Dielectric Constant @ 20°C / 1MHz</b>		15	36	77	90	190
<b>Temperature Coefficient of Capacitance</b>	ppm/°C	+100 ± 60	0 ± 30	0 ± 30	-750 ± 80	-1300 ± 120
<b>Tan δ@1MHz (Cap ≤ 1000 pF)</b>	x 10 <sup>-4</sup>	≤5	≤5	≤5	≤5	≤5
<b>Tan δ@1kHz (Cap &gt; 1000 pF)</b>	x 10 <sup>-4</sup>	≤10	≤10	≤10	≤10	≤10
<b>Dielectric Strength</b>	kVmm <sup>-1</sup> dc	22	20	15	10	10
<b>Volume Resistivity</b>	Ωm	10 <sup>13</sup>	10 <sup>13</sup>	10 <sup>13</sup>	10 <sup>13</sup>	10 <sup>13</sup>

Electrical Specification	
<b>Capacitance Range</b>	125 – 2500pF (see table)
<b>Capacitance Tolerance</b>	±20% ±10% Consult factory for other tolerances
<b>Rated RF Voltage</b>	10 kVpk (see table)
<b>Test Voltage (50Hz)</b>	√2 x Rated Voltage / 60sec
<b>RF Voltage / Current kVAr Load v Frequency</b>	See RF rating curves (ref 30°C max ambient temperature)
<b>Operating Temperature Range</b>	-25°C +95°C
<b>Maximum Relative Humidity</b>	75%







## Outline Drawing Hi-Load 10kVdc : Tag-Screw Mounting



Vertical Mounting  
Recommended

### Electrical Characteristics

Type No	Cap Value pF	TCC ppm/°C	Rated (ACpk + DC) kVpk	Rated AC kVpk	Test 50 Hz kVrms	Max POWER Rating (kVAr)	Max Current Rating (A rms)	A nom (mm)	B nom (mm)	C nom (mm)	D nom (mm)	Thread Size (mm)
04	125	+100	10	7.5	10	70	30	120	46	44	38	M6
04	150	+100	10	7.5	10	70	30	120	46	44	38	M6
04	200	+100	10	7.5	10	70	30	120	46	44	38	M6
05	330	0	10	7.5	10	70	30	120	46	44	38	M6
05	430	0	10	7.5	10	70	30	120	46	44	38	M6
05	500	0	10	7.5	10	70	30	120	46	44	38	M6
06	820	-750	10	7.5	10	50	30	120	46	44	38	M6
06	1000	-750	10	7.5	10	50	30	120	46	44	38	M6
06	1250	-750	10	7.5	10	50	30	120	46	44	38	M6
805	1600	-1300	10	7.5	10	50	30	120	46	44	38	M6
805	2000	-1300	10	7.5	10	50	30	120	46	44	38	M6
805	2500	-1300	10	7.5	10	50	30	120	46	44	38	M6



The above RF load conditions are based on the maximum body temperature rise of 45°C from an ambient temperature of 30°C.

Email technical / sales related enquiries to  
**[ruabon.sales@morganplc.com](mailto:ruabon.sales@morganplc.com)**

Please view our website :  
**[www.morganelectroceramics.com](http://www.morganelectroceramics.com)**

**Links:**

\* Power Rating & Operating Conditions

**Disclaimer:** Please note that all product, product specifications and data detailed in this brochure are subject to change without notice to improve reliability, function, design or otherwise. Morgan Advanced Materials Ltd and its affiliates does not assume any responsibility for the correctness of this information nor for damages consequent to its use. Statements regarding the suitability of products for certain types of applications are based on knowledge of typical requirements that are often placed on Morgan products in generic applications.

Morgan Advanced Materials  
**Technical Ceramics**  
Vauxhall Industrial Estate  
Ruabon  
United Kingdom LL14 6HY